

## TECHNICAL DATA SHEET

### Group II Base oil - 60N

#### Description

This series base oil utilizes Gulf's hydro treating and Texaco's MEK (Methyl-Ethyl-Ketone) de waxing process.

These base oils are widely accepted in the industrial, marine and mechanic oils as well as in automotive engine oils.

#### Technical Data

TEST ITEMS	ASTM	60N	
Specific Gravity, 15/4°C	D1298	0.8773	
Colour, Say bolt	D1500	L0.5	
Kinetic Viscosity	@40,cSt	7.498	
	@100,cSt	2.036	
Viscosity Index	D2270	66	
Flash Point, °C(COC)	D92	156	
Pour Point, °C	D97	-20.0	
Sulphur Content, wt ppm	D5453	<10	
Carbon Residue(CCR), wt%	D189	<0.01	
Copper Corrosion, 100°C/3hr	D130	1a	
TAN, mgKOH/g	D974	<0.01	
Ring Analysis,	wt%CA	8.4	
	wt%CN	D3238	42.5
	wt%CP		49.1
Aniline Point, °C	D611	77.8	

#### Packing

Flexi Tanks